



Description

BACA is an inspiring pearly smooth decorative finish offering extraordinary reflective accents. Its range of 42 shades will help you create the perfect color scheme.

Recommended For

Interior applications on plaster, embossed wall coverings, gypsum board, concrete, cement rendering, brickwork & block work. Baca can only be applied in exterior conditions when top coated with a clear sealing coat such as exterior coat (ex: Colortek Oxibond 4001, 4005 etc.)

Key Features

- No lead
- Water based
- Satin Metallic finish
- Washable (after full curing)
- Odorless
- Non-flammable
- Very low VOC content
- 6 attractive base color

Physical Properties

Solvent Type	Waterborne
Finish Type	Satin Metallic finish
Spreading Rate	Approximately 7m ² /kg depending on surface porosity and application technique
Average Dry Time	15 minutes-1 hour based on ASTM D 1640
Recoat	After 2 – 4 hours, apply as many coats as needed
Flash Point	Not Applicable
Dry Film Thickness	15 – 25 microns depending on application technique
Thinner	No thinning is required
Adhesion	Classified 4B based on ASTM 3359-B for excellent adhesion
Gloss	(20/60/85) = 5.97/ 11.1/4.27
Density	1.15 g/cm ³
Solids	30 %
Viscosity	6,000 – 10,000 cP (Spindle 4/Speed 5) based on ASTM D2196
VOC	Very low VOC content - Compliant with EU 2010 regulations maximum of 30 g/L.
Bases	500 Jupiter, 506 Hermes, 507 Poseidon, 508 Aphrodite, 509 Artemis, 510 Pallas.

Surface Preparation

All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or any other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth, dusted clean and primed with a suitable Colortek primer.

New plaster or masonry surfaces must be allowed to cure (28 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10. A soft, porous or powdery plaster indicates improper cure. Knife off any protrusions and prime the plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles.

CAUTION: Scraping or sanding surfaces of older buildings may release dust containing lead or asbestos. **EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH.** Always wear appropriate personal protective equipment during surface preparation and finish clean up of any residues by water-washing all surfaces.



Primer Systems

SURFACE TYPE	RECOMMENDED COLORTEK PRIMER
Drywall	Colortek Primer
Porous masonry	Colortek Sealer, Colortek Primer
Non porous masonry	Colortek Primer or Colortek Undercoat
Wood	Colortek Undercoat
Ferrous metal	Colortek Adhero
Non-ferrous metal	Colortek Adhero
Plaster or painted wall	Colortek Cosheen, Co-Acryl or C1A

Application Conditions

Do not apply at temperatures below 5 °C or when rain is expected.

Application Method

Stir well. Apply using a roller in three coats. Before the final coat dries exert a slight circular movement pressure using a trowel or spatula in continuous motion to reach the desired aesthetic effect.

Pack Size

- 1 US Quart – 0.85 kg
- 1 US Gallon – 3.4 kg

Shelf Life

24 months from the date of production.

Storage and Handling

Care should be taken to avoid spillage. Store in a dry area. Protect from freezing. Extreme temperatures may cause paint to become unusable. For example: freezing and thawing may cause paint to gel, and high heat may cause solid skin to form.

Safety

Use under well ventilated conditions. Do not breathe or inhale spray mist or sanding dust. Avoid skin contact; spillage on the skin should immediately be removed with suitable cleanser, soap and water. In case of eye contact, flush immediately with water for at least 15 minutes and seek medical attention immediately. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

Cleaning

Remove as much leftover product as possible from the application equipment before cleaning. Clean equipment immediately after use with warm soapy water and rinse thoroughly. Do not empty product into drains or watercourses.

Technical Assistance

Available through your local COLORTEK® Design Center or through your COLORTEK PAINTS® authorized distributor. For the location of the retailer nearest you, email us at info@colortek.eu or check our website www.colortek.eu.

Disclaimer

Product batches are subject to stringent quality control checks in conformity with ISO 9001:2008, Certificate CH12/1128.

The information submitted in this manual is correct to the best of our knowledge & experience. No liability whatsoever can be accepted on the basis of the information supplied herein.