

SCINTI

MINERAL SPARKLE EXTERIOR DECORATIVE FINISH



DESCRIPTION

Scinti is an exterior pitted decorative paint with tiny metallic inlays that will sparkle, when exposed to the sunlight, adding charm to the plastered surface.

RECOMMENDED FOR

Interior & exterior applications on plaster, gypsum board, concrete, and other properly primed and prepared surfaces.

KEY FEATURES

- No lead
- Water based
- Excellent water resistance
- Excellent durability & adhesion strength
- Odorless
- Non-flammable
- Harsh-weather proof-long life
- Reduced dirt pick-up

PHYSICAL PROPERTIES

Solvent Type	Waterborne
Finish Type	Rough, slightly pitted finish
Spreading Rate	Approximately 0.8 m ² /kg/coat – 2 coats required
Average Dry Time	Touch-dry in 2 hours based on ASTM D 1640
Recoat	24 hours
Flash Point	Not Applicable
Dry Film Thickness	1 – 3 mm depending on application technique
Thinner	No thinning is required
Adhesion	5.21 MPa based on ASTM D4541
Density	1.78 g/cm ³
Solids	82 %
Viscosity	220,000 – 260,000 cP (Spindle 96/Speed 10) based on ASTM D 2196
VOC	Very low VOC content - Compliant with EU 2010 regulations maximum of 30 g/L.
Bases	White

CERTIFICATIONS

THIS PRODUCT IS GREENGUARD GOLD CERTIFIED

The above mentioned certification determines our products compliance with the following building codes and programs amongst others:

- CHPS 2.2.2: Paints & Coatings
- LEED 2008, LEED 2009 and LEED V4
- Compliant with LIBNOR 84:1999& LIBNOR 83:1999

This product is compliant with the following standards

- UL 2818 - 2013 Gold Standard for Chemical Emissions for Building Materials, Finishes and Furnishings
- Masters Paint Institute #53 – Latex Interior Flat
- Masters Paint Institute #10 – Latex Exterior Flat

COLORTEK®
Wall and Floor Fashion

info@colortek.eu
www.colortek.eu



SCINTI

MINERAL SPARKLE EXTERIOR DECORATIVE FINISH



SURFACE PREPARATION

All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or any other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth, dusted clean and primed with a suitable Colortek primer.

New plaster or masonry surfaces must be allowed to cure (28 days) before applying base coat. Cured plaster should be hard, have a slight sheen and maximum pH of 10; soft, porous or powdery plaster indicates improper cure. Knife off any protrusions and prime the plaster before and after applying patching compound. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds. Remove any powder or loose particles.

CAUTION: Scraping or sanding surfaces of older buildings may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Always wear appropriate personal protective equipment during surface preparation and finish clean up of any residues by water-washing all surfaces.



PRIMER SYSTEMS

SURFACE TYPE	RECOMMENDED COLORTEK PRIMER
Drywall	Colortek Primer
Porous Masonry	Colortek Sealer, Colortek Primer
Non-Porous Masonry	Colortek Primer or Colortek Undercoat
Wood	Colortek Undercoat or Colortek Wood Primer
Metal	Colortek Adhero, Adhero Quick Dry, SX47 StopRust, AquaZinc
Plaster & Painted Wall	Colortek Fondo F

APPLICATION CONDITIONS

Do not apply at temperatures below 5 °C or when rain is expected.

APPLICATION METHOD

SCINTI is applied using a stainless-steel trowel. Before the final coat dries, exert a slight circular movement using the trowel in a continuous motion to reach the desired aesthetic effect.

PACK SIZE

- 1 US Drum – 25 kg

SHELF LIFE

24 months from the date of production.

STORAGE AND HANDLING

Care should be taken to avoid spillage. Store in a dry area. Protect from freezing. Extreme temperatures may cause paint to become unusable. For example: freezing and thawing may cause paint to gel, and high heat may cause solid skin to form.

SAFETY

Use under well ventilated conditions. Do not breathe or inhale spray mist or sanding dust. Avoid skin contact; spillage on the skin should immediately be removed with suitable cleanser, soap and water. In case of eye contact, flush immediately with water for at least 15 minutes and seek medical attention immediately. If you experience difficulty breathing, leave the area to obtain fresh air. If continued difficulty is experienced, get medical attention immediately.

CLEANING

Remove as much leftover product as possible from the application equipment before cleaning. Clean equipment immediately after use with warm soapy water and rinse thoroughly. Do not empty product into drains or watercourses.

TECHNICAL ASSISTANCE

Available through your local COLORTEK® Design Center or through your COLORTEK PAINTS® authorized distributor. For the location of the retailer nearest you, email us at info@colortek.eu or check our website www.colortek.eu.

DISCLAIMER

Product batches are subject to stringent quality control checks in conformity with ISO 9001:2008, Certificate CH12/1128.

The information submitted in this manual is correct to the best of our knowledge & experience. No liability whatsoever can be accepted on the basis of the information supplied herein.